

MiraVar™ 275 VOC Sealer

OPAQUE CONVERSION VARNISH SANDING SEALER WHITE

Product Code: **310668**

MiraVar™ 275 VOC Opaque Conversion Varnish Sanding Sealer is a two-part white sealer ideal for interior wood cabinetry and fine finishing.

Ideal for

- Kitchen cabinets
- Bathroom cabinets
- Wood placed in high moisture areas
- Residential table and bar tops

- CARB AIM compliant at 275 g/l VOC
- OTC Phase II compliant at 275 g/l VOC
- Utah AIM compliant at 275 g/l VOC
- NESHAP compliant—JJ (furniture)
- NESHAP compliant—QQQQ (doors & windows)

Benefits

- High solids produces excellent build
- Fills edges on MDF
- Fast, easy sanding

APPLICATION DATA

SURFACE PREPARATION: “White sand” wood with maximum 150 grit aluminum oxide sandpaper. Remove all sanding dust. Keep free of dirt, grease, silicone oils, lubricants and other contaminants.

APPLICATION EQUIPMENT: This product is designed for spray application with all types of spray equipment. Mixing or pumping equipment that is in constant contact with Conversion Varnish should be constructed of stainless steel or other anti-corrosive material.

THINNING: This product is designed for spray application at package viscosity with all equipment. If thinning is desired, use Rudd 652081 VOC Exempt Lacquer Thinner or Acetone.

Caution: Thinning with solvents will reduce film build.

Note: Thinning requirements may vary with changes in temperature and spray room conditions.

AGITATION: This product must be kept under slow, constant agitation, to ensure proper mixing.

CLEAN UP: Use Acetone or VOC compliant lacquer clean-up solvent.

FINISHING SYSTEM

MIXING DIRECTIONS: Add **4 fluid ounces** of Rudd 03-143 Catalyst per gallon. Stir well during and after adding catalyst.

POT LIFE: 8 hours @ 65–70° F.

SEAL: Apply one coat (3-4 mils wet) of MiraVar 275 VOC Conversion Varnish Opaque Sanding Sealer. Allow to dry 45 minutes*. Sand with 220/320 grit silicon carbide sandpaper before finishing.

FINISH: Apply one or two coats (3-4 mils wet) of 310601 MiraVar 275 VOC Opaque Conversion Varnish White. Sand between all coats with 220/320 grit silicon carbide sandpaper.

If desired, additional coats may be applied up to a total dry film of 5.0 dry mils.

*Dry times may vary with film thickness, temperature, humidity and air movement.

SAFETY PRECAUTIONS

Avoid breathing vapors, use a NIOSH approved cartridge respirator. Use pre-filters to avoid breathing spray particles or sanding dust.

Flammable Liquid: Keep away from heat, sparks and flame. Ensure adequate ventilation during use.

Read Safety Data Sheet and label before using.

SPECIFICATIONS

Coverage	610 square feet per gallon @ 1 mil dry film
Viscosity	30-36 Seconds (#2 Zahn @ 75° F)
Sag Resistance	5 mils vertical @ 65–70° F
Solids	55.7% by weight 5.62 lbs per gallon
VOCs (Volatile Organic Compounds)	Calculated: 1.73 lb/gal 208 g/l
HAPs (Hazardous Air Pollutants)	Pounds HAP per Pounds Solids: 0.015
Dry to Sand	45 minutes @ 65–70° F
CAUTION: Thinning will reduce film build and increase VOCs.	

APPLICATION PRECAUTIONS

- Do not use alkaline based products to clean surfaces finished with a MiraVar 275 VOC Opaque Conversion Varnish system.
- This product MUST be sanded between all coats to ensure proper adhesion. This product MUST be re-coated within 8 hours of being sanded.
- Tint only with Colortools™ or 844 Colorants. Do not exceed 8 fl oz of colorant per gallon of coating.
- This product is not recommend for exterior use.
- Finish, substrate and curing temperatures should remain above 60° F, extremes of temperature and humidity may affect product performance.
- Total film build of finishing system must not exceed 5.0 dry mils.
- This product has been tested on a limited number of substrates and over a limited number of coatings. The user is responsible for testing suitability and performance for their specific application.
- Designed for professional use by spray application only.

Shipping & Storage Information

Flash Point: -4° F Pensky-Martin

OSHA Flammability Class: Flammable Liquid—Class IB

DOT Class: Paint, 3, UN 1263, PG II



Rudd Company, Inc. · 1141 NW 50th St. · Seattle, WA 98107
ruddcompany.com · 206-789-1000

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact Rudd Company, Inc. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Rudd Company, Inc. quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.