



RUDD COMPANY, INC
Manufacturers of Quality Coatings Since 1912

www.ruddcompany.com • 206-789-1000

WATER BASE

NuWave™

WATER BASE CLEAR SANDING SEALER

Product Code: 280115

NuWave™ Water Base Clear Sanding Sealer is a single component, high solids, sealer ideal for interior wood surfaces. Rudd Nu-Wave products are the perfect solution for on-site applications.

Ideal For

- Doors and Millwork
- Fixtures & Displays
- Furniture
- Cabinets & Casegoods

- California AIM compliant at 275 g/l VOC
- OTC Phase II compliant at 275 g/l VOC
- Utah AIM compliant at 275 g/l VOC
- NESHAP compliant—JJ (furniture)
- NESHAP compliant—QQQQ (doors & windows)

Benefits

- Non-yellowing
- Very low odor
- Exceptional adhesion
- High Solids
- Fast dry
- Easy to sand
- Easy to use

APPLICATION DATA

SURFACE PREPARATION: “White sand” wood with maximum 150 grit aluminum oxide sandpaper. Remove all sanding dust. Keep free of dirt, grease, silicone oils, lubricants and other contaminants.

APPLICATION EQUIPMENT: NuWave is designed for spray application through all types of spray equipment. Use corrosion resistant equipment with water base products.

THINNING: This product is designed to spray at package viscosity. Thinning is not recommended. However, if thinning is desired, thin sparingly with water. Thinning will reduce film build and may increase grain raise.

Note: Thinning requirements may vary with changes in temperature and spray room conditions.

AGITATION: This product must be kept under slow, constant agitation, to ensure proper mixing. **Do not shake.**

CLEAN UP: Use soap and water for wet product. For dried finish clean up, use lacquer thinner.

FINISHING SYSTEM

STAIN: When staining wood, use Rudd ColorTools™ Water Base Spray Only Stain or ColorTools™ Water Base Wiping Stain.

SEAL: Apply one coat (2–4 mils wet) of NuWave Clear Lacquer Sanding Sealer. Allow to dry 45 minutes*. Sand with 220/320 grit silicon carbide sandpaper before finishing.

FINISH: Apply two coats (3–4 mils wet) of 280103 NuWave Clear Pre-Catalyzed Lacquer. Allow 45 minutes* dry time and sand with 220/320 grit silicon carbide sandpaper between coats.

If desired, additional coats may be applied up to a total dry film of 5.0 dry mils.

* Dry times will vary with film thickness, temperature, humidity and air movement.

SAFETY PRECAUTIONS

Avoid breathing vapors, use a NIOSH approved cartridge respirator. Use pre-filters to avoid breathing spray particles or sanding dust.

Read Material Safety Data Sheet and label before using.

SPECIFICATIONS

Coverage	500 square feet per gallon @ 1 dry mil film thickness
Viscosity	26 Seconds (#2 Zahn Cup @ 75° F)
Sag Resistance	4 mils vertical @ 65–70° F
Solids	34.4% by weight 2.96 lbs per gallon
VOCs (Volatile Organic Compounds)	Calculated: 1.9 lb/gal 227 -g/l
HAPs (Hazardous Air Pollutants)	Pounds HAPs per Pound Solid: 0.007 by weight
Dry to Sand	45 minutes @ 65–70° F
CAUTION: Thinning will reduce film build.	

APPLICATION PRECAUTIONS

- Dry times may vary due to environmental controls, humidity and application methods.
- Keep container closed when not in use. Store in the original container.
- Do not store above 100° F (38.8° C). Keep from freezing.
- Recommended for use with Colortools™ Water Base stains. If using over solvent base Colortools stains, allow stains to dry overnight prior to applying NuWave Clear Sealer or Lacquer.
- This coating will have a milky appearance in the can but will dry to a clear finish.
- Excessive wet film thickness will result in a “blue” coloration of film. Coloration will disappear once the coating has dried completely.
- Not recommended for use on MDF or as an exterior finish.
- The use of stainless steel application equipment is recommended.
- Finish, substrate and curing temperatures should remain above 60° F, extremes of temperature and humidity may affect product performance.
- Total film build of finishing system must not exceed 5.0 dry mils.

Shipping & Storage Information

OSHA Flammability Class: Not applicable

DOT Class: Not regulated



Rudd Company, Inc. · 1141 NW 50th St. · Seattle, WA 98107
ruddcompany.com · 206-789-1000

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact Rudd Company, Inc. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Rudd Company, Inc. quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.