



RUDD COMPANY, INC
Manufacturers of Quality Coatings Since 1912

www.ruddcompany.com • 206-789-1000

PRE-CATALYZED LACQUER

UltraClassic™ PreCat

WATER CLEAR PRE-CATALYZED LACQUER

Product Code: **653042**

UltraClassic PreCat is an economical water-clear ultra-low HAPs pre-catalyzed lacquer ideal for interior wood surfaces.

Ideal for

- Doors & Millwork
- Casegoods
- Interior Wood Work

- Federal AIM compliant at 680 g/l VOC
- NESHAP compliant—JJ (furniture)
- NESHAP compliant—QQQQ (doors & windows)

Benefits

- Water Clear
- Resistant to yellowing
- Good abrasion resistance
- Good blush resistance
- High solids
- Excellent flow and leveling
- Excellent sanding properties
- Economical self-seal system
- Ultra Low HAPs
- Low odor

APPLICATION DATA

SURFACE PREPARATION: “White sand” wood with maximum 150 grit aluminum oxide sandpaper. Remove all sanding dust. Keep free of dirt, grease, silicone oils, lubricants and other contaminants.

APPLICATION EQUIPMENT: This product is designed for spray application through all types of application equipment.

THINNING: No thinning required. This product is designed to spray at package viscosity with all application equipment. If thinning is desired, use Rudd 650870 Premium Lacquer Thinner or Acetone. For additional open time, use Rudd 650921 Retarder. Rudd Thinner & Retarder is specially formulated to achieve best results with minimal reduction.

Caution: Thinning with solvents will reduce film build and increase VOCs (unless using Acetone). Note: Thinning requirements may vary with changes in temperature and spray room conditions.

AGITATION: This product must be kept under slow, constant agitation, to ensure proper mixing and to prevent sheen variations.

CLEAN UP: Use lacquer thinner.

FINISHING SYSTEM

STAIN: When staining wood, use Rudd ColorTools™ Dye Stains, ColorTools™ Spray Only Stain, or ColorTools™ Wiping Stain.

SEAL: Apply one coat (3 -4 mils wet) of UltraClassic PreCat Clear Sanding Sealer or one coat of UltraClassic PreCat Clear Lacquer as it's own sealer. Allow to dry 20 minutes*, sand with 220/320 grit silicon carbide sandpaper before finishing.

FINISH: Apply two coats (4—6 mils wet) of UltraClassic PreCat Clear Lacquer. Allow 20 minutes* dry time and sand with 220/320 grit silicon carbide sandpaper between coats.

If desired, additional coats may be applied up to a total dry film of 5.0 dry mils.

*Dry times will vary with film thickness, temperature, humidity and air movement.

SAFETY PRECAUTIONS

Avoid breathing vapors, use a NIOSH approved cartridge respirator. Use pre-filters to avoid breathing spray particles or sanding dust.

Flammable Liquid: Keep away from heat, sparks and flame. Assure adequate ventilation during use.

Read Material Safety Data Sheet and label before using.

KCMA FINISH TEST

Vinegar	No Visual Effect
Lemon Juice	No Visual Effect
Orange Juice	No Visual Effect
Grape Juice	No Visual Effect
Catsup	No Visual Effect
Olive Oil	No Visual Effect
100 Proof Alcohol	No Visual Effect
Coffee	No Visual Effect
Water Ring	Slight marking at 190° F after 1 hour
Edge Soak	Passed 24 hr KCMA test with no softening, discoloration or film defects

*** Contact your Sales Representative for available stock sheens and package sizes.***

SPECIFICATIONS

Coverage	325 square feet per gallon @ 1 mil dry film thickness
Viscosity	25–30 seconds (#2 Zahn Cup @ 77° F)
Sag Resistance	5 mils vertical @ 65–70° F
Solids*	27–27.7% by weight 2.07–2.10 lbs per gallon
VOCs* (Volatile Organic Compounds)	Calculated: 4.7–4.72 lb/gal 564–566 g/l
HAPs* (Hazardous Air Pollutants)	Pounds HAP per Pounds Solid: 0.029–0.030
Dry to Sand	20 minutes @ 65–70° F
Block Free	8 hours @ 65–70° F
*Variations depend on gloss CAUTION: Thinning will reduce film build and increase VOCs.	

APPLICATION PRECAUTIONS

- UltraClassic PreCat Clear Lacquer has a shelf life of approximately 12 months from date of manufacture.
- Usability and performance may not be determined from viscosity. Shelf life will vary with storage conditions.
- Do not use UltraClassic PreCat Clear Lacquer as a topcoat over stearated sanding sealers. Formulated for use as a self-seal system.
- Do not use UltraClassic PreCat Clear Lacquer in heated spray equipment.
- This product is not recommended for exterior use.
- Clear finishes will not prevent natural (unstained) wood from changing color over time.
- Finish, substrate and curing temperatures should remain above 60° F, extremes of temperature and humidity may affect product performance.
- Total film build of system must not exceed 5.0 dry mils.
- This product has been tested on a limited number of substrates and over a limited number of coatings. The user is responsible for testing suitability and performance for their specific application.
- Designed for professional use by spray application only

Shipping & Storage Information

Flash Point: -4° F Pensky-Martin

OSHA Flammability Class: Flammable Liquid—Class IB

DOT Class: Paint, 3, UM 1263, PG II



Rudd Company, Inc. · 1141 NW 50th St. · Seattle, WA 98107
ruddcompany.com · 206-789-1000

To the best of our knowledge the technical data contained herein are true and accurate at the date of issuance and are subject to change without prior notice. User must contact Rudd Company, Inc. to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Rudd Company, Inc. quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY THE SELLER, EXPRESSED OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.